Fate and transport processes

Transport parameters for PETN, tetryl, nitroglycerin



Adsorption Kinetics Relative Stability: PETN>tetryl>nitroglycerin

Fate and transport processes

Dissolution kinetics



Octol: 70% HMX, 30% TNT Comp B: 59.5 % RDX, 39.5% TNT, 1% wax LX-14 95.5% HMX, 4.5% Estane